



PD-705

High Build WB Flexible Surfer

SX1047

SX1047 High Build WB Flexible Surfer was developed to offer a flexible waterborne surfer with excellent performance on urethanes, plastic, fiberglass and other substrates.



Features

- Ready to spray
- Easy to sand
- Non-flammable
- Meets stringent air quality regulations

Compatible Surfaces

- Properly cleaned and sanded plastic
- Properly cleaned and sanded fiberglass
- Cured and sanded OEM finishes (except lacquer)

Related Products

- SX1002 Sanding Paste
- SX1004 Plastic Cleaner and Prep
- SXA1030 Guide Coat Black

Compatible Topcoats

- CONCEPT® (DCC) Acrylic Urethane
- CONCEPT® LV (CLV) Acrylic Urethane Color
- Delstar® / Delthane® (DAR/DXR80)
- Delstar® Acrylic Enamel
- Deltron® 2000 (DBC) Basecoat
- Deltron® (DBU) Universal Basecoat
- Omni™ (MBC) Acrylic Basecoat
- Omni™ (MTK) Acrylic Urethane
- Omni™ (MLV) Low VOC Urethane
- Omni™ (MAE) Acrylic Enamel
- Omni™ (MAE/MH) Acrylic Enamel
- Omni™ (MCV) Acrylic Urethane
- Omni™ (MCV) High Solids Urethane
- Omni™ (MCV) Basecoat
- Global (BC) Basecoat Color
- Global (DG) Direct Gloss Color
- Global (DGLV) Direct Gloss LV Color
- Delta® 2800 (DHS) 2.8 VOC Polyurethane
- Delta® 3500 (DUHS) High Solids Polyurethane
- Delta® (DUHS) High Solids Polyurethane Basecoat
- Delta® (DFHS) Fast Dry High Solids Polyurethane
- Delta® (DGHS) Chemical Resistant Polyurethane
- Delta® (DSS) Medium Solids Polyurethane
- Delta® (DVHS) Fast Dry 2.8 VOC Polyurethane



Application Data

Surface Preparation:



1. Apply **SX1002 Sanding Paste** and abrade with a gray scuff pad, then rinse thoroughly with water. Blow off surface.
2. Clean with **SX1004 Plastic Cleaner and Prep** using a lint free towel wiping in one direction.

Application Procedure:



1. Apply 2 medium coats of **SX1047 High Build WB Flexible Surfacer**.
2. When surfacer dries, apply **SXA1030 Guide Coat Black**.
3. Dry sand with 320-400 grit paper.
4. Wipe and blow off surface. Tack clean with a tack cloth.
5. Apply the PPG paint system of choice. Refer to the appropriate topcoat bulletin for specific instructions.

NOTE: Do not wet sand.

Drying Times:



- | | |
|----------------|---------------|
| Between Coats: | 5-10 minutes |
| Dry to Sand: | 45-60 minutes |

Fluid Tip:



1.8 - 2.3 mm or equivalent

Properties:

Product	Packaged VOC (lbs./US Gal.)	Volume Solids (RTS)	SQ. FT. Coverage @ 1 mil (100% transfer efficiency)
SX1047	1.7	30.25	485

See Material Safety Data Sheet and Labels for additional safety information and handling instructions.

EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION (304) 843-1300. IN CANADA (514) 645-1320.

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the public. Products mentioned may be hazardous and should only be used according to directions, while observing precautions and warning statements listed on label. Statements and methods described are based upon the best information and practices known to PPG Industries. Procedures for applications mentioned are suggestions only and are not to be construed as representations or warranties as to performance, results, or fitness for any intended use, nor does PPG Industries warrant freedom from patent infringement in the use of any formula or process set forth herein.

PPG Industries

World Leaders In Automotive Finishes

PPG Industries
19699 Progress Drive
Strongsville, OH 44149

PPG Canada Inc.
2301 Royal Windsor Dr.
Mississauga, Ontario L5J 1K5